

université
de BORDEAUX



Suspensions near the jamming transition

Guillaume Ovarlez

guillaume.ovarlez@u-bordeaux.fr



Concentrated suspensions near jamming

Standard fresh concrete




Solid (can be shaped) at rest

Self-compacting concrete



Liquid (flows under its own weight)


Concentrated suspensions vs. model materials



Static particle packings

Slow deposition


Random loose packing



$$\phi = 0.52-0.55$$

Small vibrations


Random close packing



$$\phi = 0.62-0.64$$

Periodic shearing

Hexagonal close packed configuration






$$\phi = 0.74$$

Source:
nucleus.iaea.org


Particle fraction
 ϕ





Sheared particle packings




Macroscopic behavior of **viscous nonBrownian** suspensions




Often shear thinning...





Sometimes « ideal » = linear



Macroscopic behavior of **viscous nonBrownian** suspensions




shear stress: $\tau = \eta_s(\phi) \eta_0 \dot{\gamma}$



Etcheverry (2022)

Suspensions viscosity: hydrodynamics + contacts


Simulations: Gallier et al. (2014)



Interparticle friction ($\mu_p \approx 0.5$) necessary for agreement with exp.

For frictional grains, **contact contribution dominant for $\phi \geq 40\%$**


Role of interparticle friction




$$\eta_s(\phi) \propto \eta_s(0) \left(1 - \frac{\phi}{\phi_j}\right)^{-2}$$

ϕ_j decreases with interparticle friction

ϕ_j = critical state vol. fraction of granular materials




Mari et al, JOR (2014)





Peters et al., JFM (2016)

Impact of particle shape




Suspended in a concentrated emulsion





Impact of particle shape

Identification of rolling resistance as a shape parameter in sheared granular media

Nicolas Estrada,^{1,*} Emilien Azéma,^{2,†} Farhang Radjai,² and Alfredo Taboada³



ϕ_j decreases
with rolling friction



Singh et al. (2020)

Impact of polydispersity

Construction and Building Materials 161 (2018) 340–353


Contents lists available at [ScienceDirect](#)



ELSEVIER

Construction and Building Materials


journal homepage: www.elsevier.com/locate/conbuildmat



Review

Understanding the role of particle packing characteristics in rheo-physical properties of cementitious suspensions: A literature review



Iman Mehdipour, Kamal H. Khayat*



Computations for hardened concrete based on random close packing ϕ_{rcp}
→ what about ϕ_j ?

Bidisperse suspensions



Use packing model for rcp \rightarrow same equation for ϕ_j



Polydisperse suspensions

Pednekar, Chun, Morris, J. Rheol (2018):

Polydisperse suspension \equiv « statistically equivalent » suspension



Use model of bidisperse suspension to compute jamming fraction ϕ_j

$$\text{then } \eta_s(\phi) \propto \eta_s(0) \left(1 - \frac{\phi}{\phi_j}\right)^{-2}$$

Increasing the jamming fraction


Reminder: $\phi_j(\mu_p)$ decreases when interparticle friction μ_p increases

Need to kill friction

decrease μ_p

Add polymer


Creates a repulsive barrier





e.g., cement

Toussaint et al., Rheol Acta 2009


prevent from contact formation
Play with flow configuration



« Frictionless » suspensions





Stabilized Silica particles
Lootens et al. (2005)



Side effect : **shear-thickening**
 → something happens at the contact scale



Shear-thickening: frictionless / frictional transition

<http://blairlab.georgetown.edu>




Short range repulsive colloidal force
introduces rate dependence
→ **no friction / friction transition**



Shear-thickening: frictionless / frictional transition



Short range repulsive colloidal force
introduces rate dependence
 → **no friction / friction transition**




Shear-jamming: fluid / solid transition





Hodgson et al., JOR (2022)

Shear-induced **inhomogeneities** at shear thickening




Vol. fraction maps
from X-ray imaging

Gholami et al (2018)



homogeneous
extrusion




**inhomogeneous
extrusion**

O'Neill et al. (2019) ; (2024?)

Shear-induced migration in brief

Leighton & Acrivos 1987, Nott & Brady 1994...



⇒ diphasic description; migration driven by $\nabla \sigma^p$

Crucial role of interparticle contacts

⇒ enhanced @ shear thickening


Increasing the jamming fraction

Reminder: $\phi_j(\mu_p)$ decreases when interparticle friction μ_p increases


Need to kill friction

decrease μ_p
Add polymer


Creates a repulsive barrier



prevent from contact formation
Play with flow configuration




Macroscopic behavior, **contacts** and **microstructure**



Response to shear reversal

Contacts
(in compression)
are broken
(in traction)
before being reformed




Increasing the jamming fraction

Reminder: $\phi_j(\mu_p)$ decreases when interparticle friction μ_p increases

Need to kill friction


decrease μ_p
Add polymer

Creates a repulsive barrier



prevent from contact formation
Play with flow configuration


Vibrations



Fluidization of a granular sediment

Hanotin et al. , PRL 2015

orthogonal flow superimposed



Shear-thickening suppression

Lin et al., PNAS 2016


Rheology of vibrated suspensions : phenomenology



Silica suspension (Solvay), $\phi^{wt} = 0.29$




Vibrations and formulation



Silica suspension (Solvay)

Conclusion



Rich nonlinear behavior

Crucial role of interparticle contacts

Beware inhomogeneities

Various levers: physico-chemistry and process